TERRITORIO MADERA PU

Gauge	EN ISO 24346 (EN 428)	2.0mm
Wear Layer	EN ISO 24340 (EN 428)	0.2mm
Plank Size	EN ISO 24342 (EN 427)	36 @ 101.6 x 914.4mm = 3.34m² 24 @ 152.4 x 914.4mm = 3.34m² 18 @ 152.4 x 1219.2mm = 3.34m² 15 @ 184.2 x 1219.2mm = 3.37m²
Tile Size	EN ISO 24342 (EN 427)	36 @ 304.8 x 304.8mm = 3.34m² 18 @ 304.8 x 609.6mm = 3.34m² 16 @ 457.2 x 457.2mm = 3.34m²
Total Weight	EN ISO 23997 (EN 430)	3680g/m²
General Performance	EN 649 EN ISO 10582	Conforms Conforms
Use Area	EN ISO 10582 (EN 685)	22
Behaviour to Fire	EN 13501-1	Bfl-S1
Resistance to Chemicals	EN ISO 26987 (EN 423)	Resistant depending on concentration and time of exposure. In case of increased impact of oils, grease, acids, alkalis and other aggressive chemicals, please contact us.
Abrasion Resistance	EN 649 EN ISO 10582	Group T Type 1
Slip Resistance	EN 13893 DIN 51130 AS 4586	Class DS (dry condition) R10 R10 For safety flooring with sustainable wet slip resistance, refer to Expona Control or the Polysafe ranges.
Residual Indentation	EN ISO 24343-1 (EN 433)	<0.1mm
Dimensional Stability	EN ISO 23999 (EN 434)	≤0.1% max
Thermal Conductivity	ISO 8302	Suitable for underfloor heating. Max 27°C.
Light Fastness	ISO 105-B02	(Method 3) ≥6
Castor Chair (continuous use)	ISO 4918 (EN 425)	Suitable
Electrical Behaviour (body voltage)	EN 1815	≤2kV Classified as 'antistatic'
VOC Emissions	Indoor Air Comfort GOLD AgBB VOC test FloorScore Finnish M1 Classification	Eurofins certified product Very low emissions Certified product Pass
Responsible Sourcing	BES 6001	Good

Environmentally Preferable Flooring - Polyflor Colonia PUR achieves BRE Global A rating (ENP 429). Generic EN 15804 Environmental Product Declaration (EPD) available on request. It is 100% recyclable and contains average 40% recycled material. Recyclable via the Recofloor scheme. Visit www.polyflor.com/sustainability.

PUR - Polyflor Colonia PUR features a high quality, cross-linked polyurethane reinforcement, UV cured to provide a low-cost, polish free maintenance regime for the lifetime of the flooring.

For information regarding handling and installation, adhesives, maintenance, applications, chemical resistance and product warranty, consult **Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com.**
The data presented is correct at the time of printing. For latest information, please visit our website **polyflor.com**.
Decoration and shade may vary slightly from the samples shown.

100% RECYCLABLE
40% RECYCLED MATERIAL

BS EN 14041 EN 14041

POLYFLOR™ COVERING THE WORLD

UK Sales Direct: +44 (0)161 767 1122 | Export Sales Direct: +44 (0)161 767 1913
Sample Requests: +44 (0)161 767 2551 | email: info@polyflor.com | **www.polyflor.com**

James Halstead™ FLOORING

Sept 2021