



| Technical parameter | Standard | Unit | Result |
|---------------------------------------|-----------------|---|--------------------------------------|
| DESCRIPTION | | | |
| Construction | | | compact heterogeneous |
| Total thickness | EN 428 | mm | 2,0 |
| Wear layer thickness | EN 429 | mm | 0,7 |
| Width of roll | EN 426 | m | 2 , 4 |
| Length of roll | EN 426 | lm | 20 |
| Total weight | EN 430 | kg/m2 | 2,2 |
| CLASSIFICATION | | | |
| Product specification | EN 649 | | ✓ |
| European classification | EN 685 | class | 34/43 |
| Residual indentation | EN 433 | max. mm | 0,1 |
| Dimensional stability | EN 434 | max.% | 0,2 |
| Light fastness | EN 20105 B02 | grade | 6 |
| PERFORMANCE | | | |
| Abrasion group | MSZ EN 660-1 | class | T |
| Fire resistance | EN 13501-1 | class | Bfl-s1 |
| | Gost 30402-94 | | G1 |
| Slip resistance | DIN 51130 | | R9 |
| | EN 13893 | | DS |
| Electrical resistance | EN 1815 | kV | < 2 |
| | EN 1081 | Ω | ≤ 10 ⁹ |
| Chemical resistance | EN 423 | | ✓ |
| Bacterial resistance | EN ISO846:1999 | | ✓ |
| Castor chair resistance | EN 425 | | ✓ |
| Anti-bacterial and fungicid treatment | |  | graboSAN |
| Enviromental attributes | |  | Solvent and heavy metal free product |
| Seaming method | | | heat or cold weld |
| Warranty | | year | 10 |
| CE MARKING | EN 14041 | | ✓ |